

# tonerplastics

## Pearl PLA 3D Filament Data Sheet

### Poly lactide and Polyester Blend

Pearl is a high gloss PLA and polyester blend filament designed to produce high quality models with a silky pearl finish. Due to the added polyester, it is much less brittle than PLA. Pearl also maintains several of PLA's unique and desirable printing qualities such as low odor, high detail and low warpage. It does not require a heated bed to be printed, although when printing without one the use of a raft is recommended.

Material Production Specifications	
Nominal Outer Diameter, mm	1.75/2.88
OD Tolerance, mm	±0.08
Ovality, mm	< 0.08

[1] Ovality is defined as the difference between the smallest and largest outer diameters

### Applications

- Fine detail prints
- General purpose 3D printing
- Applications where high rigidity is required

### Recommended Printer Settings

- Extruder Temperature: 230-250 °C
- Printing Speed: 50-100 mm/s
- Bed Temperature: 70-90 °C
- Bed Adhesion: Hair Spray or PVA Glue

### Additional Information

- Standard Sizes Available: 1.75/2.88mm
- Custom packaging methods available upon request
- Spool Weight: 1kg., 1lb., 5lb., and 10lb
- All filaments are sealed with desiccants

### Regulatory Compliance

- RoHS
- REACH
- California Proposition 65

### Disclaimer:

The above information is provided in good faith. Toner Plastics assumes no obligation or liability for the accuracy or completeness of the information supplied in this document. It is solely the customers responsibility to determine if the product and information in this document are appropriate for the customers end use. Responsibility for the use, storage, handling, and disposal of the products herein is that of the purchaser or end user.